

# BONE ASH, FAKE

A.K.A.

# TRICALCIUM

# PHOSPHATE



CaO	54.30%
P <sub>2</sub> O <sub>5</sub>	45.70

**Characteristics:**

Tricalcium phosphate is otherwise known as “Fake Bone Ash” and can be used to approximate the fluxing action of bone ash.