

CLAY, PLASTIC VITROX

SiO ₂	78.03 %
Al ₂ O ₃	12.07
Fe ₂ O ₃	0.24
TiO ₂	0.05
MgO	1.29
CaO	0.50
K ₂ O	5.03
Na ₂ O	0.33
L.O.I.	2.46
P.C.E.	